

New  
Series

# LANDOLT- BÖRNSTEIN

Numerical Data  
and Functional Relationships  
in Science and Technology

GROUP III

VOLUME 43

Condensed  
Matter

## Crystal Structures of Inorganic Compounds

SUBVOLUME A

Structure Types

Part 7

Space Groups (160)  $R3m$  – (156)  $P3m1$



Springer

Landolt-Börnstein

Numerical Data and Functional Relationships in Science and Technology

*New Series* / Editor in Chief: W. Martienssen

Group III: Condensed Matter

Volume 43

# Crystal Structures of Inorganic Compounds

Subvolume A

Structure Types

Part 7

Space groups (160)  $R3m$  – (156)  $P3m1$

Editors:

P. Villars, K. Cenzual

Contributors:

J. Daams, R. Gladyshevskii, O. Shcherban

and

V. Dubenskyy, V. Kuprysyuk, O. Pavlyuk, I. Savysyuk, S. Stoyko

 Springer

ISSN 1615-1925 (Condensed Matter)

ISBN 978-3-540-69948-4 Springer Berlin Heidelberg New York

Library of Congress Cataloging in Publication Data

Zahlenwerte und Funktionen aus Naturwissenschaften und Technik, Neue Serie

Editor in Chief: W. Martienssen

Vol. III/43A7: Editors: P. Villars, K. Cenzual

At head of title: Landolt-Börnstein. Added t.p.: Numerical data and functional relationships in science and technology.

Tables chiefly in English.

Intended to supersede the Physikalisch-chemische Tabellen by H. Landolt and R. Börnstein of which the 6th ed. began publication in 1950

under title: Zahlenwerte und Funktionen aus Physik, Chemie, Astronomie, Geophysik und Technik.

Vols. published after v. 1 of group I have imprint: Berlin, New York, Springer-Verlag

Includes bibliographies.

I. Physics--Tables. 2. Chemistry--Tables. 3. Engineering--Tables.

I. Börnstein, R. (Richard), 1852-1913. II. Landolt, H. (Hans), 1831-1910.

III. Physikalisch-chemische Tabellen. IV. Title: Numerical data and functional relationships in science and technology.

QC61.23 502'.12 62-53136

This work is subject to copyright. All rights are reserved, whether the whole or part of the material is concerned, specifically the rights of translation, reprinting, reuse of illustrations, recitation, broadcasting, reproduction on microfilm or in other ways, and storage in data banks. Duplication of this publication or parts thereof is permitted only under the provisions of the German Copyright Law of September 9, 1965, in its current version, and permission for use must always be obtained from Springer-Verlag. Violations are liable for prosecution act under German Copyright Law.

Springer is a part of Springer Science+Business Media

springeronline.com

© Springer-Verlag Berlin Heidelberg 2009

Printed in Germany

The use of general descriptive names, registered names, trademarks, etc. in this publication does not imply, even in the absence of a specific statement, that such names are exempt from the relevant protective laws and regulations and therefore free for general use.

*Product Liability:* The data and other information in this handbook have been carefully extracted and evaluated by experts from the original literature. Furthermore, they have been checked for correctness by authors and the editorial staff before printing. Nevertheless, the publisher can give no guarantee for the correctness of the data and information provided. In any individual case of application, the respective user must check the correctness by consulting other relevant sources of information.

Cover layout: Erich Kirchner, Heidelberg

Typesetting: Authors and Redaktion Landolt-Börnstein, Heidelberg

Printing and binding: AZ-Druck, Kempten

SPIN: 1092 0602 63/3020 - 5 4 3 2 1 0 – Printed on acid-free paper

## **Editors**

### **P. Villars**

Materials Phases Data System  
CH-6354 Vitznau, Switzerland  
e-mail: villars@mpds.ch

### **K. Cenzual**

Department of Inorganic, Analytical and Applied Chemistry  
Geneva University  
CH-1211 Geneva, Switzerland  
e-mail: Karin.Cenzual@chiam.unige.ch

## **Contributors to Subvolume III/43 A 7**

### **J. Daams**

Materials Phases Data System  
CH-6354 Vitznau, Switzerland

### **R. Gladyshevskii**

Department of Inorganic Chemistry  
Ivan Franko National University of Lviv  
UA-79005 Lviv, Ukraine

### **O. Shcherban**

Scientific Consulting Company Structure-Properties  
UA-79026 Lviv, Ukraine

and

### **V. Dubenskyy, V. Kuprysyuk, O. Pavlyuk, I. Savysyuk, S. Stoyko**

Scientific Consulting Company Structure-Properties  
UA-79026 Lviv, Ukraine

## **Landolt-Börnstein**

### **Springer**

Tiergartenstr. 17, D-69121 Heidelberg, Germany

fax: +49 (6221) 487-8648

e-mail: [Redaktion.Landolt-Boernstein@springer.com](mailto:Redaktion.Landolt-Boernstein@springer.com)

### **Internet**

<http://www.landolt-boernstein.com>

# Preface

In the 1970s Landolt-Börnstein published a series of volumes containing crystallographic data for organic (III/5 Structure Data of Organic Crystals), intermetallic (III/6 Structure Data of Elements and Intermetallic phases) and inorganic compounds (III/7 Crystal Structure Data of Inorganic Compounds). During the 30 years that have passed, the experimental methods leading to a complete structure determination have considerably improved and the large number of crystal structures known today justifies the publication of a new compilation.

The present volume will cover both intermetallic and classical inorganic compounds, a clear limit having been drawn by excluding compounds that contain C-H bonds. Whereas the earlier edition listed space group/crystal system and cell parameters for different classes of compounds, we have here chosen a different approach by grouping known crystal structures into structure types. The structure type concept is widely used among inorganic compounds, where the number of isotypic compounds can reach several hundreds. The first subvolumes will contain complete crystallographic data sets, including atom coordinates, that represent distinct structure types, whereas the last subvolumes will list cell parameters of isotypic compounds. The crystallographic data are accompanied by remarks and crystallographic features common to isotypic compounds, such as the atomic environments, a brief description of the main structural features, and drawings of selected structure types.

In the definition used here, structures belonging to the same structure type crystallize in the same space group, have similar cell parameters and similar representative atom coordinates. The latter criterion requires that they are isopointal, i.e. they have the same Wyckoff sequence (sequence of Wyckoff positions). Following this scheme, the structure types are ordered according to the space group number and the Wyckoff sequence. The present subvolume, the sixth of the series, contains data for some 700 hexagonal and trigonal (space groups # 166 from Pearson symbol *hR153* to # 160 up to Pearson symbol *R3m*) structure types, reported up to the year 2005.

We would like to thank the coauthors for their contribution and all other collaborators on the databases TYPIX and Pauling File, who have, through the years, helped in compiling and analyzing the large number of structural data that constitute the basis of this work.

# Introduction

## *Structure Types*

### 1 Subject matter

---

#### 1.1 General remarks on the contents

---

Inorganic compounds are here defined as compounds containing no C-H bonds.

The first series of subvolumes will contain complete crystallographic data sets representative of structure types found among inorganic compounds. The second series of subvolumes will contain lists of compounds crystallizing with these types.

The compilations TYPIX [1], Pearson's Handbook [2a] and Pauling File Binaries Edition [2b] constitute a valuable basis for this work, but all data have been reprocessed from the original publications. Our aim is to cover the literature published up to two years before the release of the subvolume.

#### 1.2 Structure type concept

---

According to the definition used here, isotypic compounds crystallize in the same space group, have similar cell parameter ratios, and occupy the same Wyckoff positions in the standardized description with the same or similar values of the atom coordinates [3]. If all these criteria are fulfilled, the coordination polyhedra should be similar and the main structural features respected. It follows from the definition that isotypic structures are isopointal (same Wyckoff positions), however, two isopointal structures are not necessarily isotypic. The last step in distinguishing different structure types is subjective and we have sometimes been guided by what is usually considered in the literature.

No distinction is made between structures with fully and partly occupied atom sites. Except for binary compounds, protons are not taken into consideration, so that e.g. ammonium and alkaline metal compounds are considered to be isotypic. Disordered structures are included in the classification and different models for site splitting can sometimes subdivide a conventional structure type into several types. Ordering variants are distinguished, mixed occupations by two or several chemical elements being considered as the same dummy element, independently of the proportions.

#### 1.3 Data selection and checking

---

Each structure type is represented by a, if available, recent refinement of the structure of the compound for which this particular atom arrangement was first reported. In those cases where two isotypic structures were reported the same year, the date of submission of the manuscript was taken as criterion. In exceptional cases, preference has been given to a structure with less vacancies, or a lower degree of disorder. Thesis works have not been considered, and conference abstracts only in a few cases.

No systematic effort has been made to select the most recent refinement, and a more accurate refinement has sometimes been preferred to a routine phase analysis, without any claim on having selected here the "best" refinement. Preference has been given to structure determinations corresponding to ambient conditions.

The data have been submitted to extensive computer-aided checking and, as far as possible, misprints in the crystallographic data have been corrected. When relevant, the data have been transformed to a space group taking into consideration all symmetry elements effectively present in the structure. A few obviously wrong structures have been excluded from the compilation. References are sometimes added to more recent literature where the correctness of the structure determination is questioned, but no exhaustive literature search has been carried out in this sense.

## 1.4 Standardization of crystallographic data

The crystallographic data have been standardized following a method proposed by Parthé and Gelato [4], using the program STRUCTURE TIDY [5]. The standardization procedure applies criteria to select the space group setting, the cell parameters, the origin of the coordinate system, the representative atom coordinates, and the order of the atom sites.

- (1) The coordinate system must be right-handed and refer to a space group setting defined in the International Tables for Crystallography [6], with the following additional constraints
  - triclinic space groups: Niggli-reduced cell
  - monoclinic space groups:  $b$ -axis unique, "best" cell
  - orthorhombic space groups:  $a \leq b \leq c$ , when not fixed by the space group setting
  - trigonal space groups with  $R$ -lattice: triple hexagonal cell
  - space groups with two origin choices: origin choice 2 (origin at inversion center)
  - enantiomorphic space groups: smallest index of the relevant screw axis
- (2) The representative triplet of each atom site must obey a series of eliminative conditions listed below.
  - first triplet in International Tables for Crystallography [6]
  - $0 \leq x, y, z < 1$
  - minimum value of  $(x^2 + y^2 + z^2)$
  - minimum value of  $x$
  - minimum value of  $y$
  - minimum value of  $z$
- (3) For the 148 non-polar space groups there are between 1 and 24 possibilities to rotate, invert or shift the coordinate system, respecting the conditions listed above. For polar space groups the standardization program will prepare data sets where one atom site after the other, belonging to the "lowest Wyckoff set" (set of Wyckoff sites containing the earliest letters in the alphabet), fixes the origin on the polar axis. In each case, the standardized data set is selected based on the following eliminative conditions:
  - minimum value of  $\Gamma = \sum (x_j^2 + y_j^2 + z_j^2)^{1/2}$  summed over all atom sites
  - minimum value of  $\sum x_j$  summed over all atom sites
  - minimum value of  $\sum y_j$  summed over all atom sites
  - minimum value of  $\sum z_j$  summed over all atom sites
  - minimum value of  $x_n^2 + y_n^2 + z_n^2$  for the  $n^{\text{th}}$  atom site

- (4) Finally, the atom sites are reordered according to the eliminative criteria:
  - inverse alphabetic order of the Wyckoff letters
  - increasing  $x$
  - increasing  $y$
  - increasing  $z$
- (5) On extending the standardization procedure, originally designed for intermetallic compounds, to other inorganic compounds, it appeared sensible to consider protons apart, since their positions are often not determined. For compounds with more than two elements, the proton positions, when determined, are consequently not taken into consideration for the selection of the standardized description, but are listed at the end of the table of atom coordinates, respecting the same criteria for their internal ordering and selection of representative triplets as indicated above. It follows that proton positions are not considered in the Wyckoff sequence, and also not in the sum of multiplicities included in the Pearson symbol.

## 1.5 Atomic environments

---

The definition of the atomic environments (AE) [7] is based on the method of Brunner and Schwarzenbach [8], where the interatomic distances between an atom site and its nearest neighbors are plotted in a histogram. In the general case, the Atomic Environment Type (AET) is the polyhedron formed by the atoms to the left of the maximum gap appearing in the histogram. In those cases where the maximum gap rule leads to AEs with some of the selected atoms inside the polyhedron formed by the others, or to AEs with atoms located in the faces of the polyhedron, the maximum-convex-volume rule is applied. This rule is defined as the maximum volume around only one central atom enclosed by convex faces, with all the atoms situated at the intersections of at least three faces. The same rule was also used in those cases where no clear maximum gap was present. Whenever two or more equal or similar gaps were observed, the number of different AETs in a structure type was kept as small as possible.

For fully ordered intermetallic structures, the AETs can be assimilated to the conventional coordination polyhedra. Differences occur based on the fact that the atomic environment is a purely geometric concept and differences in chemical bonding, oxidation state (cations and anions are not distinguished) or atomic radii are not taken into consideration. All atom sites are further treated as being fully occupied, so that, for instance, the atomic environment of the phosphorus atom in an orientationally disordered phosphate group may be a cube, whereas the conventional coordination polyhedron is a tetrahedron.

The AETs are here designated by the name of the coordination polyhedron (when simple) and its composition. Positions belonging to atom sites with mixed occupation are represented by the majority element, or by the first element in alphabetic order, if identical proportions are reported. Protons are only taken into consideration in exceptional cases.

## 2 Selection and arrangement of the data

---

### 2.1 Framed data

---

- Chemical formula. Selected chemical units are distinguished and a particular order is adopted for the elements, which constitutes a compromise for chemical compounds ranging from intermetallic to ionic, including some coordination and covalent compounds. The coefficients are such defined that the number of formula units in the unit cell is an integer which takes into consideration at least the factor corresponding to the Bravais lattice.
- Pearson symbol [9]. A lower-case letter defines the crystal system (*a* for anorthic = triclinic, *m* for monoclinic, *o* for orthorhombic, *t* for tetragonal, *h* for hexagonal or trigonal, and *c* for cubic) and an upper-case letter the Bravais lattice (*P* for primitive, *S* for side-face centered, *F* for all-face centered, *I* for body centered, and *R* for rhombohedrally centered). The integer number following these two characters corresponds to the sum of the site multiplicities of all partly or fully occupied Wyckoff positions. Note that following the recommendations of a subcommission of the International Union of Crystallography [10], we use the letter *S*, which groups *A*, *B* and *C*-face centered lattices, and that the triple hexagonal cell is considered for *R*-type Bravais lattices.
- Space group and Wyckoff sequence. The number assigned to the space group in the International Tables for Crystallography [6], indicated within parentheses, is followed by the Hermann-Mauguin symbol corresponding to the standardized data. The Wyckoff sequence lists the Wyckoff letters of all, fully or partly occupied atom sites in the structure. The letters are written in inverse alphabetic order, a superscript number being added when a particular Wyckoff position is present more than once.

### 2.2 General information about the structure type

---

- Alternative type names. These include chemical formulas of isotopic compounds that are sometimes used in the literature to designate the structure type, but also mineral names, colloquial names used within particular structure families, and Strukturbericht notations [11]. The alternative type names are listed in alphabetic order in the subject index.
- References. Each chemical formula is followed by a reference to the first structure determination.
- Structural features. A short description of the structure type, referring to the type-defining compound, emphasizes particular structural features such as the arrangement of close-packed layers or coordination polyhedra. Close relationships to other structure types, such as ordered substitution or filling-up of interstices, are sometimes mentioned.

### 2.3 General information about the selected data set

---

- First author(s) of the reference from which the crystallographic data are taken.
- Refined composition. An alphabetically sorted chemical formula as computed from the crystallographic data set.

- Cell parameters  $a$ ,  $b$ ,  $c$ ,  $\alpha$ ,  $\beta$ ,  $\gamma$ , computed cell volume  $V$ , interaxial ratio(s), and the number of formula units per unit cell  $Z$ . The latter applies to the refined composition and to the chemical formula given in the frame, but not necessarily to the alternative type names.

## 2.4 Table of atom coordinates

---

- Atom site. The sites are named after the chemical element they are occupied by, or  $M$  if occupied by a mixture of two or several elements. The numbering is continuous through the table, starting from 1, and independent of the site occupation.
- Site multiplicity and Wyckoff letter, according to the International Tables for Crystallography [6].
- Site symmetry. Point symmetry (symmetry implying no translational component,  $m$  for mirror plane, 2 for 2-fold axis, etc.).
- Fractional positional coordinates with respect to the three crystallographic axes:  $x/a$ ,  $y/b$ ,  $z/c$ .
- Site occupancy. Normalized to 1 (omitted) for a fully occupied site.
- Atomic environment type (AET) as defined under 1.5.

## 2.5 Footnote to the table of atom coordinates

---

- When relevant, occupation of mixed sites normalized to a total occupancy 1.
- When relevant, transformation from the published data applied by the standardization procedure.
- When specified in the original publication, condensed information about the experimental procedure: single crystal/powder/thin film, diffractometer/photographs, X-rays/neutrons/electrons, the lowest of the published conventional reliability factors for the structure refinement  $R/wR/R_p/wR_p/R_B$ , temperature  $T$ , pressure  $p$ .

## 2.6 Remarks

---

The remarks given here include information about the stability range of the type-defining compound, the origin of mineral specimens, particularities concerning the structure refinement, short interatomic distances, corrections applied to the published data, related literature, etc.

## 2.7 References

---

Literature references are given for all publications mentioned in the data set. The journal names are abbreviated following the recommendations of the Chemical Abstracts Service.

## 2.8 Figures

---

Figures emphasizing particular structural features are presented for commonly occurring structure types. Some less common structure types are also shown, in order to illustrate the great variety of inorganic structures.

## 2.9 Order of the structure types

---

The data sets representing the distinct structure types are arranged according to features characterizing the standardized crystallographic description:

- decreasing order of the number assigned to the space group in the International Tables for Crystallography [6]
- increasing sum of site multiplicities (included in the Pearson symbol)
- alphabetic order of the Wyckoff sequence
- increasing value of the interaxial ratio  $c/a$

An extensive index listing various type names found in the literature will help the user to find a particular structure type.

## 3 References used in the introduction

---

- [1] Parthé E., Gelato L., Chabot B., Penzo M., Cenozal K., Gladyshevskii R., Gmelin Handbook of Inorganic and Organometallic Chemistry, 8th Ed., TYPPIX - Standardized Data and Crystal Chemical Characterization of Inorganic Structure Types, 4 volumes, Heidelberg: Springer, 1993, 1994.
- [2a] Pearson's Handbook of Crystallographic Data for Intermetallic Phases, 4 volumes, Eds. Villars P. and Calvert L., Materials Park (OH 44073): ASM International, 1991.
- [2b] Pauling File Binaries Edition, CD-ROM, Eds. Villars P. (editor-in-chief), Cenozal K., Daams J., Hulliger F., Massalski T., Okamoto H., Osaki K., Prince A. (editors), Materials Park, OH 44073, ASM International, 2002.
- [3] Lima de Faria J., Hellner E., Makowicky E., Liebau F., Parthé E. (1990), Acta Crystallogr. A 46, 1–11.
- [4] Parthé E., Gelato L.M. (1984), Acta Crystallogr. A 40, 169–183; Parthé E., Gelato L.M. (1985), Acta Crystallogr. A 41, 142–151; Parthé E., Cenozal K., Gladyshevskii R. (1993), J. Alloys Compd. 197, 291–301.
- [5] Gelato L.M., Parthé E. (1987), J. Appl. Crystallogr. 20, 139–143.
- [6] International Tables for Crystallography, Vol. A, Ed. T. Hahn, Dordrecht: Kluwer Academic Publishers, 2002.
- [7] Daams J.L.C., in Intermetallic Compounds, Vol. 1, Eds. J.H. Westbrook and R.L. Fleischer, New York: John Wiley and Sons, 1994.
- [8] Brunner G.O., Schwarzenbach D. (1971), Z. Kristallogr. 133, 127–133.
- [9] Pearson W.B., Handbook of Lattice Spacings and Structure of Metals, New York: Pergamon, 1967.
- [10] De Wolff P.P., Belov N.V., Bertaut E.F., Buerger M.J., Donnay J.D.H., Fischer W., Hahn T., Koptsik V.A., Mackay A.L., Wondratschek H., Wilson A.J.C., Abrahams S.C. (1985), Acta Crystallogr. A 21, 278–280.
- [11] Strukturberichte. Supplement to Z. Kristallogr. (1913–1939). Vol. 1–7. Leipzig: Akad. Verlagsgesellschaft, 1931–1943.

# Structure type index by space group

## *Structure Types*

Space group (160)  $R\bar{3}m$

ZnS 48R<sub>1</sub>

ZnS 48R<sub>2</sub>

ZnS 48R<sub>3</sub>

ZnS 48R<sub>4</sub>

ZnS 48R<sub>5</sub>

ZnS 48R<sub>6</sub>

ZnS 48R<sub>7</sub>

ZnS 48R<sub>8</sub>

ZnS 48R<sub>9</sub>

TiS<sub>1.73</sub> 48R

CdI<sub>2</sub> 66R<sub>1</sub>

CdI<sub>2</sub> 66R<sub>2</sub>

CdI<sub>2</sub> 66R<sub>3</sub>

CdI<sub>2</sub> 66R<sub>4</sub>

CdI<sub>2</sub> 66R<sub>5</sub>

CdI<sub>2</sub> 66R<sub>6</sub>

CdI<sub>2</sub> 66R<sub>7</sub>

Na<sub>0.42</sub>Mg<sub>0.67</sub>Eu<sub>0.63</sub>Al<sub>10.33</sub>O<sub>17</sub>

[Pt(NH<sub>3</sub>)<sub>5</sub>Cl]Cl<sub>3</sub>·H<sub>2</sub>O

S<sub>3</sub>N<sub>5</sub>PF<sub>2</sub>

Ag<sub>4</sub>Ge<sub>7</sub>O<sub>16</sub>·6H<sub>2</sub>O

Na<sub>3</sub>(NH<sub>4</sub>)Ge<sub>7</sub>O<sub>16</sub>·6H<sub>2</sub>O

Na<sub>4</sub>(TiO)<sub>4</sub>(SiO<sub>4</sub>)<sub>3</sub>·6H<sub>2</sub>O

SiC 51R<sub>1</sub>

SiC 51R<sub>2</sub>

SiC 51R<sub>3</sub>

Na<sub>1.62</sub>Li<sub>0.31</sub>Al<sub>10.69</sub>O<sub>17</sub>

Nd<sub>0.54</sub>Mg<sub>0.62</sub>Al<sub>10.38</sub>O<sub>17</sub>

Na<sub>4</sub>Ge<sub>7</sub>O<sub>16</sub>·6H<sub>2</sub>O

ZnS 54R<sub>1</sub>

ZnS 54R<sub>2</sub>

ZnS 54R<sub>3</sub>

ZnS 54R<sub>4</sub>

ZnS 54R<sub>5</sub>

ZnS 54R<sub>6</sub>

ZnS 54R<sub>7</sub>

ZnS 54R<sub>8</sub>

ZnS 54R<sub>9</sub>

ZnS 54R<sub>10</sub>

ZnS 54R<sub>11</sub>

CdI<sub>2</sub> 72R<sub>1</sub>

CdI<sub>2</sub> 72R<sub>2</sub>

CdI<sub>2</sub> 72R<sub>3</sub>  
Na<sub>1.29</sub>Mg<sub>0.67</sub>Eu<sub>0.19</sub>Al<sub>10.33</sub>O<sub>17</sub>  
Gd<sub>0.56</sub>Mg<sub>0.67</sub>Al<sub>10.33</sub>O<sub>17</sub>  
SiC 57R  
CdI<sub>2</sub> 78R<sub>1</sub>  
CdI<sub>2</sub> 78R<sub>2</sub>  
Na<sub>2.6</sub>Rb<sub>0.8</sub>H<sub>0.6</sub>Ge<sub>7</sub>O<sub>16</sub>·6H<sub>2</sub>O  
ZnS 60R<sub>1</sub>  
ZnS 60R<sub>2</sub>  
ZnS 60R<sub>3</sub>  
ZnS 60R<sub>4</sub>  
ZnS 60R<sub>5</sub>  
ZnS 60R<sub>6</sub>  
ZnS 60R<sub>7</sub>  
ZnS 60R<sub>8</sub>  
ZnS 60R<sub>9</sub>  
ZnS 60R<sub>10</sub>  
ZnS 60R<sub>11</sub>  
ZnS 60R<sub>12</sub>  
ZnS 60R<sub>13</sub>  
ZnS 60R<sub>14</sub>  
ZnS 60R<sub>15</sub>  
ZnS 60R<sub>16</sub>  
ZnS 60R<sub>17</sub>  
ZnS 60R<sub>18</sub>  
ZnS 60R<sub>19</sub>  
In<sub>3</sub>Sb<sub>5</sub>O<sub>12</sub>  
CdI<sub>2</sub> 84R<sub>1</sub>  
CdI<sub>2</sub> 84R<sub>2</sub>  
CdI<sub>2</sub> 84R<sub>3</sub>  
CdI<sub>2</sub> 84R<sub>4</sub>  
CdI<sub>2</sub> 84R<sub>5</sub>  
CdI<sub>2</sub> 84R<sub>6</sub>  
ZnS 66R<sub>1</sub>  
ZnS 66R<sub>2</sub>  
ZnS 66R<sub>3</sub>  
ZnS 66R<sub>4</sub>  
ZnS 66R<sub>5</sub>  
CdI<sub>2</sub> 90R  
Na<sub>2</sub>CaPO<sub>4</sub>F  
SiC 69R<sub>1</sub>  
SiC 69R<sub>2</sub>  
ZnS 72R<sub>1</sub>  
ZnS 72R<sub>2</sub>  
ZnS 72R<sub>3</sub>  
ZnS 72R<sub>4</sub>  
ZnS 72R<sub>5</sub>  
ZnS 72R<sub>6</sub>  
ZnS 72R<sub>7</sub>  
ZnS 72R<sub>8</sub>  
ZnS 72R<sub>9</sub>

ZnS 72R<sub>10</sub>  
ZnS 72R<sub>11</sub>  
ZnS 72R<sub>12</sub>  
ZnS 72R<sub>13</sub>  
ZnS 72R<sub>14</sub>  
ZnS 72R<sub>15</sub>  
ZnS 72R<sub>16</sub>  
ZnS 72R<sub>17</sub>  
ZnS 72R<sub>18</sub>  
ZnS 72R<sub>19</sub>  
ZnS 72R<sub>20</sub>  
CdI<sub>2</sub> 96R<sub>1</sub>  
CdI<sub>2</sub> 96R<sub>2</sub>  
Cs<sub>7</sub>Na<sub>4</sub>Mo<sub>4</sub>Se<sub>4</sub>(CN)<sub>12</sub>Cl<sub>3</sub>  
(Fe<sub>1.58</sub>Al<sub>1.42</sub>)Al<sub>6</sub>Si<sub>6</sub>O<sub>18.42</sub>(BO<sub>3</sub>)<sub>3</sub>(OH)<sub>3.58</sub>  
NaMg<sub>6</sub>Al<sub>3</sub>Si<sub>6</sub>B<sub>3</sub>(O,OH)<sub>30</sub>  
SiC 75R  
NaMg<sub>3</sub>Al<sub>6</sub>Si<sub>6</sub>O<sub>18</sub>(BO<sub>3</sub>)<sub>3</sub>(OH)<sub>3</sub>F  
CdI<sub>2</sub> 102R<sub>1</sub>  
CdI<sub>2</sub> 102R<sub>2</sub>  
Cu<sub>7.55</sub>Al<sub>4.80</sub>  
ZnS 78R<sub>1</sub>  
ZnS 78R<sub>2</sub>  
ZnS 78R<sub>3</sub>  
ZnS 78R<sub>4</sub>  
ZnS 78R<sub>5</sub>  
ZnS 78R<sub>6</sub>  
Cu<sub>8.03</sub>Al<sub>4.68</sub>  
Li<sub>2</sub>CaAl<sub>7</sub>Si<sub>6</sub>O<sub>18</sub>(BO<sub>3</sub>)<sub>3</sub>(OH)<sub>4</sub>  
NaLi<sub>1.5</sub>Al<sub>7.5</sub>Si<sub>6</sub>O<sub>18</sub>(BO<sub>3</sub>)<sub>3</sub>(OH)<sub>3</sub>F  
CdI<sub>2</sub> 108R<sub>1</sub>  
CdI<sub>2</sub> 108R<sub>2</sub>  
La<sub>3.266</sub>Mn<sub>1.1</sub>S<sub>6</sub> (see  
SiC 84R  
ZnS 84R<sub>1</sub>  
ZnS 84R<sub>2</sub>  
ZnS 84R<sub>3</sub>  
ZnS 84R<sub>4</sub>  
SiC 87R  
SiC 90R  
ZnS 90R<sub>1</sub>  
ZnS 90R<sub>2</sub>  
ZnS 90R<sub>3</sub>  
CdI<sub>2</sub> 120R<sub>1</sub>  
CdI<sub>2</sub> 120R<sub>2</sub>  
SiC 93R<sub>1</sub>  
SiC 93R<sub>2</sub>  
Ca<sub>3</sub>SiO<sub>5</sub> 9R  
SiC 96R  
ZnS 96R<sub>1</sub>  
ZnS 96R<sub>2</sub>

$\text{Nd}_{12,4}\text{Mg}_{0,6}\text{Mo}_{13}\text{O}_{36}$   
 ZnS 102R  
 $\text{Bi}_{8,1}\text{V}_{0,9}\text{O}_{14}$   
 SiC 105R  
 $\text{CsNaVOSi}_4\text{O}_{10}\cdot 4\text{H}_2\text{O}$   
 ZnS 108R<sub>1</sub>  
 ZnS 108R<sub>2</sub>  
 ZnS 108R<sub>3</sub>  
 SiC 111R  
 ZnS 114R<sub>1</sub>  
 ZnS 114R<sub>2</sub>  
 ZnS 114R<sub>3</sub>  
 ZnS 114R<sub>4</sub>  
 $\text{Pb}_{2,31}\text{Nb}_2\text{O}_{7,31}$   
 $\text{Ca}_3\text{GeO}_5$  9R  
 $(\text{REE},\text{Y},\text{Ca},\text{Na},\text{Th})_{16}(\text{Fe},\text{Ti})\text{B}_3(\text{Si},\text{P})_7\text{O}_{34}(\text{OH})_4\text{F}_{10}$   
 SiC 120R  
 ZnS 120R<sub>1</sub>  
 ZnS 120R<sub>2</sub>  
 ZnS 120R<sub>3</sub>  
 $(\text{Ca},\text{REE},\text{Th})_{15}\text{Fe}(\text{SiO}_4)_3\text{B}_3\text{Si}_3\text{O}_{18}(\text{BO}_3)(\text{AsO}_4)(\text{AsO}_3)_x(\text{NaF}_3)_{1-x}\text{F}_7\cdot 0.2\text{H}_2\text{O}$   
 SiC 126R  
 SiC 141R  
 SiC 147R  
 SiC 150R<sub>1</sub>  
 SiC 150R<sub>2</sub>  
 ZnS 162R  
 $\text{Ca}_3\text{GeO}_5$  24R  
 $\text{Pb}_{2,44}\text{Nb}_2\text{O}_{7,44}$   
 SiC 174R  
 $\text{Na}_{12}\text{Ca}_6\text{Zr}_3\text{Fe}_3\text{Si}_{26}\text{O}_{72}(\text{OH})_2$   
 SiC 189R  
 $\text{Na}_{12}\text{Ca}_6\text{Zr}_3\text{Fe}_3\text{Si}_{25}\text{O}_{69}(\text{OH})_{3,5}\text{Cl}_{0,5}$   
 $\text{Na}_{12}\text{Sr}_3\text{Ca}_6\text{Zr}_3\text{Fe}_3\text{NbSi}_{25}\text{O}_{73}(\text{O},\text{OH},\text{H}_2\text{O})_3\text{Cl}_2$   
 $\text{Na}_{12}(\text{Ce},\text{La},\text{Sr})_x\text{Ca}_6\text{Zr}_3\text{Mn}_3\text{WSi}_{25}\text{O}_{73}(\text{OH},\text{Cl})_2\text{CO}_3$   
 $(\text{Na},\text{REE},\text{Sr},\text{K},\text{Y})_{15}(\text{Ca},\text{Mn},\text{REE})_6\text{Zr}_3(\text{Mn},\text{Fe})_3\text{NbSi}_{25}\text{O}_{73}(\text{O},\text{OH},\text{H}_2\text{O})_3(\text{OH},\text{Cl})_2$   
 $(\text{Na},\text{REE},\text{K},\text{Sr})_{15}(\text{Ca},\text{Mn},\text{Y},\text{REE})_6\text{Zr}_3(\text{Mn},\text{Fe})_3(\text{Nb},\text{Ta})\text{Si}_{25}\text{O}_{73}(\text{O},\text{OH},\text{H}_2\text{O})_3(\text{Cl},\text{OH})_2$   
 $(\text{Na},\text{Ca},\text{Sr},\text{REE})_{15}(\text{Ca},\text{Y})_6(\text{Mn},\text{Fe})_3(\text{Zr},\text{Ti})_3(\text{Si},\text{Nb})\text{Si}_{25}\text{O}_{73}(\text{O},\text{OH},\text{H}_2\text{O})_3(\text{OH},\text{Cl})_2$   
 $(\text{Na},\text{Sr},\text{Ca},\text{K})_{15}\text{Ca}_6\text{Zr}_3(\text{Fe},\text{Mn})_3(\text{W},\text{Nb})\text{Si}_{25}\text{O}_{73}(\text{O},\text{OH},\text{H}_2\text{O})_3(\text{OH},\text{Cl})_2$   
 $\text{Na}_{12}(\text{K},\text{Sr},\text{Ce})_3\text{Ca}_6\text{Zr}_3\text{Mn}_3\text{NbSi}_{25}\text{O}_{72}(\text{O},\text{OH})_4(\text{H}_2\text{O},\text{CO}_3,\text{Cl})_2$   
 $(\text{H}_3\text{O})_7\text{Na}_{3,8}\text{K}_{2,2}\text{Ca}_6\text{Zr}_{3,8}\text{Fe}_{1,2}\text{Si}_{25}\text{O}_{60}(\text{O},\text{OH})_{18}\text{Cl}_{1,5}$   
 $(\text{Na},\text{REE},\text{K},\text{Sr})_{15}(\text{Ca},\text{Mn},\text{REE},\text{Y})_6\text{Zr}_3(\text{Mn},\text{Fe})_3(\text{Si},\text{Nb})\text{Si}_{25}\text{O}_{73}(\text{O},\text{OH},\text{H}_2\text{O})_3(\text{OH},\text{Cl})_2$   
 $\text{Na}_{11}\text{Ca}_9\text{Zr}_3(\text{Fe},\text{Ti},\text{Zr},\text{Hf})_3(\text{Si},\text{Mn})(\text{Nb},\text{Si})\text{Si}_{24}\text{O}_{72}(\text{O},\text{OH})_{4,15}\text{Cl}_{0,2}\cdot 3\text{H}_2\text{O}$   
 $(\text{Na},\text{REE},\text{K},\text{Sr})_{15}(\text{Ca},\text{Mn},\text{Y},\text{REE})_6(\text{Zr},\text{Ti})_3(\text{Mn},\text{Fe},\text{Al})_3\text{NbSi}_{25}\text{O}_{73}(\text{O},\text{OH},\text{H}_2\text{O})_3(\text{F},\text{Cl},\text{OH})_2$   
 $(\text{H}_3\text{O})_{3,3}(\text{Na},\text{K},\text{Sr})_{8,7}(\text{Ca},\text{Mn})_6\text{Zr}_3(\text{Zr},\text{Si})_{0,7}(\text{Fe},\text{Na})_3\text{Si}_{24}\text{O}_{66}(\text{O},\text{OH})_6(\text{OH},\text{Cl})_{5,4}\cdot 2\text{H}_2\text{O}$   
 $(\text{Na},\text{K})_{14}(\text{Ca},\text{Mn})_6\text{Zr}_3(\text{Fe},\text{Ta})_{1,8}(\text{Si},\text{Nb},\text{W})(\text{Si},\text{Al},\text{Ti})\text{Si}_{24}\text{O}_{72}(\text{OH},\text{O})_{3,5}\text{Cl}_{0,8}\cdot 1.2\text{H}_2\text{O}$   
 $\text{Na}_{12}(\text{Mn},\text{Sr},\text{REE})_3\text{Ca}_6\text{Zr}_3\text{Fe}_3\text{NbSi}_{25}\text{O}_{72}(\text{O},\text{OH})_4(\text{O},\text{OH},\text{F})\text{Cl}\cdot \text{H}_2\text{O}$   
 $(\text{Na},\text{K},\text{Sr})_{16}(\text{Ca},\text{Mn},\text{Fe})_6\text{Zr}_3(\text{Zr},\text{Si},\text{Al},\text{Ti},\text{Nb})_x\text{Si}_{24}\text{O}_{72}(\text{O},\text{OH})_4\text{Cl}_{0,5}\cdot \text{H}_2\text{O}$   
 $\text{Pr}_4\text{Mo}_9\text{O}_{18}$   
 $(\text{Na},\text{REE},\text{K},\text{Ca})_{15}(\text{Ca},\text{Mn},\text{Y},\text{REE})_6\text{Zr}_3(\text{Fe},\text{Mn})_3\text{NbSi}_{25}\text{O}_{73}(\text{O},\text{OH},\text{H}_2\text{O})_3(\text{OH},\text{Cl})_2$   
 $\text{Na}_{12}(\text{Sr},\text{Na})_3(\text{Ca},\text{Mn},\text{REE})_6\text{Zr}_3(\text{Fe},\text{Nb},\text{Mn})_x\text{Si}_{25}\text{O}_{66}(\text{OH},\text{O},\text{Cl})_{11}\cdot 11\text{H}_2\text{O}$

$\text{Na}_{10}\text{Ca}_9\text{Zr}_3\text{Fe}_2\text{NbSi}_{25}\text{O}_{72}(\text{OH})_3\text{CO}_3\cdot\text{H}_2\text{O}$   
 $\text{Na}_{14.3}(\text{Na},\text{Sr},\text{K})_3(\text{Ca},\text{Mn},\text{Ce},\text{Na})_6\text{Zr}_3(\text{Nb},\text{Ti},\text{Fe})_x(\text{Mn},\text{Si},\text{Al})\text{Si}_{25}\text{O}_{72}(\text{OH})_{3.3}\text{Cl}_{0.7}\cdot 1.6\text{H}_2\text{O}$   
 $\text{Na}_9(\text{Na},\text{K},\text{Sr})_6\text{Ca}_6\text{Zr}_3(\text{Fe},\text{Mn})_3(\text{Si},\text{Nb},\text{H})_2\text{Si}_{24}\text{O}_{72}(\text{OH})_{3.1}\text{Cl}_{1.4}$   
 SiC 261R  
 $(\text{Na},\text{Ca},\text{K},\text{Ce})_{15}\text{Ca}_6\text{Zr}_3(\text{Fe},\text{Mn})_3(\text{Si},\text{Nb},\text{Ti})\text{Si}_{24}\text{O}_{72}(\text{OH})_{2.2}(\text{CO}_3)_{0.9}\text{Cl}_{0.5}\cdot 0.5\text{H}_2\text{O}$   
 $\text{K}_{1.3}\text{Na}_{14.3}\text{Sr}_{0.3}\text{Ca}_6\text{Zr}_3\text{Mn}_{0.5}\text{Fe}_2(\text{Si}_{1.3}\text{Al}_{0.3}\text{H}_{0.4})\text{Si}_{24}\text{O}_{72}(\text{OH})_{2.1}\text{Cl}_{1.7}$   
 SiC 393R  
 SiC 411R  
 $\text{K}_8\text{Na}_{27}\text{Ca}_{12}\text{Zr}_6\text{Fe}_3\text{Si}_{52}\text{O}_{144}(\text{O},\text{OH},\text{H}_2\text{O})_6\text{Cl}_2$   
 $\text{Na}_{36}(\text{Ca},\text{Mn})_6(\text{Ca},\text{Na},\text{Ce})_6(\text{Zr},\text{Ti})_6(\text{Ti},\text{Fe})_x(\text{Si},\text{Mn})_4\text{Si}_{48}\text{O}_{144}(\text{OH},\text{Cl})_{5.7}\cdot x\text{H}_2\text{O}$   
 SiC 519R

### Space group (159) *P31c*

$\text{K}_2\text{HgI}_4\cdot n\text{H}_2\text{O}$   
 $\text{KLiSO}_4$  form II  
 $\text{KNaTeO}_3\cdot 3\text{H}_2\text{O}$   
 $\text{Na}_{0.5}\text{Scl}_3$   
 $\text{NaPb}_2(\text{CO}_3)_2\text{OH}$   
 $\text{YbBaCo}_4\text{O}_7$  rt  
 $\text{Si}_3\text{N}_4$   $\alpha$   
 $\text{Nd}_{0.33}\text{Al}_{2.1}\text{Si}_{9.9}\text{N}_{14.9}\text{O}_{1.1}$   
 $\text{KLiSO}_4$  form II  
 $\text{LaNi}_5\text{H}_7$   
 $\text{Ag}_2\text{CO}_3$   $\beta$   
 $\text{Rb}_2\text{TeW}_3\text{O}_{12}$   
 $\text{Ag}_3(\text{NSO}_2)_3\cdot 3\text{H}_2\text{O}$   
 $\text{Al}_2(\text{SeO}_3)_3\cdot 6\text{H}_2\text{O}$   
 $\text{Ag}_4\text{Hg}_5\text{O}_2(\text{AsO}_4)_2$   
 $\text{LiNaSO}_4$   $\beta$   
 $\text{CdMg}_2\text{Cl}_6\cdot 12\text{H}_2\text{O}$   
 $\text{Cs}_2$   
 $(\text{NH}_4)_2\text{W}_3(\mu_3\text{-S})(\mu_2\text{-S})_3(\text{S}_4)_3(\text{NH}_3)_3\cdot \text{H}_2\text{O}$   
 $\text{Ba}_7\text{Cu}_3\text{H}_{17}$   
 $\text{Cu}_6\text{Al}(\text{SO}_4)(\text{OH})_{12}\text{Cl}\cdot 3\text{H}_2\text{O}$   
 $\text{Cs}_4\text{Ba}(\text{PO}_3)_6$   
 $\text{Dy}_{0.62}\text{Ni}_2\text{Ga}_{5.25}\text{Ge}$   
 $\text{Cu}_6\text{Al}(\text{SO}_4)(\text{OH})_{12}\text{Cl}\cdot 3\text{H}_2\text{O}$   
 $\text{Cu}_6\text{Al}(\text{SO}_4)(\text{OH})_{12}\text{Cl}\cdot 3\text{H}_2\text{O}$   
 $\text{Pb}_3\text{B}_{10}\text{O}_{16}(\text{OH})_4$   
 $\text{Re}_3\text{S}_7\text{Cl}_7$   
 $\text{Na}_2\text{V}_3\text{O}_7$   
 $(\text{H}_3\text{O})$   
 $\text{Hg}_8\text{Se}_4\text{O}_{16}\cdot \text{H}_2\text{O}$   
 $\text{KBa}_6\text{Ga}_7\text{Zn}_4\text{O}_{21}$   
 $\text{Cs}_3\text{Mo}_5\text{P}_6\text{O}_{25}$   
 $\text{K}_5\text{NaTi}_6\text{Se}_{27}$   
 $\text{Er}_6\text{Si}_{11}\text{N}_{20}\text{O}$   
 $\text{Er}_{6.25}\text{Si}_{11}\text{N}_{20.76}\text{O}_{0.24}$   
 $\text{Nd}_7\text{Al}_3\text{Si}_8\text{N}_{20}\text{O}$   
 $\text{SeBr}_4$   $\alpha$   
 $(\text{NH}_4)\text{H}_8\text{Fe}_3(\text{PO}_4)_6\cdot 6\text{H}_2\text{O}$

BaGe(Ge<sub>2.125</sub>Si<sub>0.875</sub>)O<sub>9</sub>  
 CsTi<sub>8</sub>F<sub>33</sub>  
 Pb<sub>3</sub>CaAl<sub>2</sub>Si<sub>10</sub>O<sub>27</sub>·3H<sub>2</sub>O  
 Pb<sub>3</sub>CaAl<sub>2</sub>Si<sub>10</sub>O<sub>27</sub>·4H<sub>2</sub>O (see  
 Li<sub>8</sub>(HPO<sub>4</sub>)(BePO<sub>4</sub>)<sub>6</sub>·H<sub>2</sub>O  
 Na<sub>8</sub>Al<sub>6</sub>Ge<sub>6</sub>O<sub>24</sub>(CO<sub>3</sub>)·3H<sub>2</sub>O  
 Na<sub>8</sub>Al<sub>6</sub>Ge<sub>6</sub>O<sub>24</sub>(CO<sub>3</sub>)·2H<sub>2</sub>O  
 Na<sub>8</sub>Al<sub>6</sub>Ge<sub>6</sub>O<sub>24</sub>(CO<sub>3</sub>)·2H<sub>2</sub>O  
 (Na,K)<sub>7</sub>CaAl<sub>6</sub>Si<sub>6</sub>O<sub>24</sub>(S<sub>3</sub>)<sub>1.5</sub>·H<sub>2</sub>O  
 Ca<sub>6</sub>  
 Mg<sub>8</sub>SiW<sub>9</sub>O<sub>37</sub>·12H<sub>2</sub>O  
 Ba<sub>3</sub>MoN<sub>4</sub> ht  
 Ca<sub>6</sub>(Fe<sub>0.6</sub>Al<sub>0.2</sub>Mn<sub>0.2</sub>)<sub>2</sub>(SO<sub>4</sub>)<sub>2.7</sub>  
 (Cs,K)<sub>2</sub>VOSi<sub>4</sub>O<sub>10</sub>·3H<sub>2</sub>O  
 Mg<sub>8</sub>SiW<sub>9</sub>O<sub>37</sub>·24.5H<sub>2</sub>O  
 Bi<sub>24</sub>Cr<sub>8</sub>O<sub>57</sub>(OH)<sub>6</sub>·3H<sub>2</sub>O  
 Ir<sub>9</sub>Al<sub>28</sub>  
 (Na,K)<sub>22</sub>Ca<sub>10</sub>Al<sub>24</sub>Si<sub>24</sub>O<sub>96</sub>(SO<sub>4</sub>)<sub>6</sub>Cl<sub>5.8</sub>F<sub>0.2</sub>  
 K<sub>2</sub>Na<sub>3</sub>(Mn,Fe,Na)<sub>4</sub>Si<sub>9</sub>(O,OH)<sub>27</sub>(OH)<sub>2</sub>·nH<sub>2</sub>O  
 K<sub>11</sub>Na<sub>31</sub>Ca<sub>6</sub>Al<sub>36</sub>Si<sub>36</sub>O<sub>144</sub>(SO<sub>4</sub>)<sub>8</sub>Cl<sub>2</sub>·6H<sub>2</sub>O  
 K<sub>16</sub>Na<sub>42</sub>Ca<sub>6</sub>Al<sub>48</sub>Si<sub>48</sub>O<sub>192</sub>(SO<sub>4</sub>)<sub>10</sub>Cl<sub>2</sub>·5H<sub>2</sub>O

#### Space group (158) *P3c1*

RuCl<sub>3</sub> β  
 Be<sub>2</sub>(BO<sub>3</sub>)OH·H<sub>2</sub>O 2T  
 Ba<sub>5</sub>Ga<sub>6</sub>H<sub>2</sub>  
 Mn<sub>2</sub>Zn<sub>2</sub>Nb<sub>2</sub>O<sub>9</sub>  
 Mn<sub>5</sub>Ge<sub>2</sub>  
 LiGaO<sub>2</sub>·8H<sub>2</sub>O  
 PO(OPF<sub>2</sub>)<sub>3</sub> trigonal  
 (Na,Li)<sub>7</sub>Th<sub>6</sub>F<sub>31</sub>  
 K<sub>0.4</sub>(Cu<sub>0.9</sub>HCO<sub>3</sub>)<sub>2</sub>(OH)<sub>2</sub>·1.66H<sub>2</sub>O  
 Na<sub>0.5</sub>HCa<sub>5.1</sub>MgFe<sub>2.7</sub>Al<sub>6.1</sub>Si<sub>12</sub>O<sub>36</sub>(OH)<sub>12</sub>(CO<sub>3</sub>)<sub>1.2</sub>·12H<sub>2</sub>O  
 Mn<sub>23</sub>Ge<sub>9</sub>  
 Ba<sub>5</sub>CuI<sub>3</sub>O<sub>12</sub>

#### Space group (157) *P31m*

Na<sub>2</sub>ZnCl<sub>4</sub>·3H<sub>2</sub>O  
 TiO<sub>0.3</sub>H<sub>0.1</sub>  
 Cu<sub>2</sub>SiS<sub>3</sub> ht  
 Ag<sub>5</sub>Pb<sub>2</sub>O<sub>6</sub>  
 Fe<sub>4</sub>SiO<sub>5</sub>(OH)<sub>4</sub> 1T  
 Cs<sub>4</sub>Au<sub>6</sub>S<sub>5</sub>  
 LaNi<sub>5</sub>H<sub>7</sub>  
 Cs<sub>3</sub>As<sub>5</sub>O<sub>9</sub>  
 AuCd rt  
 Mg<sub>3</sub>Si<sub>2</sub>O<sub>5</sub>(OH)<sub>4</sub> 1T  
 K<sub>3</sub>Nb<sub>3</sub>B<sub>2</sub>O<sub>12</sub>  
 K<sub>3</sub>V<sub>5</sub>O<sub>14</sub>  
 Li<sub>17</sub>Ag<sub>3</sub>Sn<sub>6</sub>  
 Pb(ReO<sub>4</sub>)<sub>2</sub>

$\text{Pb}_3(\text{CO}_3)_2(\text{OH})_2$   
 $\text{K}_3\text{V}_5\text{O}_{14}$   
 Pb  
 $\text{Mg}_{12}(\text{HPO}_4)(\text{PO}_4)_5(\text{OH},\text{O})_6$   
 $\text{Mg}_{12}(\text{HPO}_4,\text{CO}_3)(\text{PO}_4)_5(\text{OH},\text{O})_6$   
 $\text{Ba}_{21}\text{Al}_{40}$   
 $\text{Ba}_{10}(\text{MnFeF}_{10.15}\text{Cl}_{0.85})_3\text{F}_{0.85}\text{Cl}_{1.15}$   
 $\text{C}(\text{NH}_2)_3\text{Al}(\text{SO}_4)_2 \cdot 6\text{H}_2\text{O}$   
 $\text{Mn}_{13}\text{SbSi}_2\text{O}_{24}$   
 $\text{Na}_{15}(\text{SO}_4)_5\text{F}_4\text{Cl}$   
 $\text{Na}_{21}(\text{SO}_4)_7\text{F}_6\text{Cl}$   
 $\text{K}_3\text{Nb}_3\text{B}_2\text{O}_{12}$

### Space group (156) *P3m1*

$\text{Si}_6\text{H}_3(\text{OH})_3$  2D  
 BiTel  
 $\text{Ni}_2\text{H}$   
 $\text{LiPtH}_{0.66}$   
 CuI  $\beta$   
 SrAlSiH  
 $\text{CuScS}_2$   
 $\text{AsTe}_{0.5}\text{O}_2$   
 $\text{LaNdO}_{1.75}\text{S}$   
 $\text{NaLiZnO}_2$   
 $\text{SnS}_2$  4H  
 $\text{CeCuSnH}_{0.33}$   
 $\text{CdInGaS}_4$   
 $\text{ZnIn}_2\text{S}_4$  form I  
 $\text{Li}_{1.05}\text{Ca}_{0.95}\text{Sn}$   
 $\text{PbI}_2$  6H  
 $\text{CdI}_2$  6H<sub>1</sub>  
 $\text{CuIn}_7\text{Se}_{11}$   
 $\text{LiNpO}_2\text{CO}_3 \cdot 2\text{H}_2\text{O}$   
 $\text{Zn}_3\text{In}_2\text{S}_6$  form Ib  
 $\text{Nb}_3\text{SBr}_7$   
 CuI 6H  
 $\text{CdI}_2$  8H  
 $\text{NbSe}_2$  4s(d)  
 $\text{KSn}_2\text{F}_5$  form II  
 $\text{LiYMo}_3\text{O}_8$   
 $\text{KNaSO}_4$   
 $\text{Cs}_3\text{Sb}_2\text{I}_9$  trigonal  
 $\text{Li}(\text{H}_2\text{O})\text{TiS}_2$   
 $\text{PbI}_2$  10H<sub>1</sub>  
 $\text{PbI}_2$  10H<sub>3</sub>  
 $\text{CdI}_2$  10H<sub>1</sub>  
 $\text{CdI}_2$  10H<sub>4</sub>  
 $\text{CdI}_2$  10H<sub>6</sub>  
 $\text{YBa}_2\text{Cu}_3\text{O}_{6.5}$   
 $\text{BaTiO}_{2.67}$   
 AgI 8H

Zn<sub>5</sub>In<sub>2</sub>S<sub>8</sub> 8H<sub>8</sub>  
ZnS 8H<sub>1</sub>  
ZnS 8H<sub>2</sub>  
SiC 9H  
CdI<sub>2</sub> 12H<sub>1</sub>  
CdI<sub>2</sub> 12H<sub>2</sub>  
CdI<sub>2</sub> 12H<sub>3</sub>  
CdI<sub>2</sub> 12H<sub>4</sub>  
CdI<sub>2</sub> 12H<sub>7</sub>  
CdI<sub>2</sub> 12H<sub>8</sub>  
CdI<sub>2</sub> 12H<sub>10</sub>  
(Cd<sub>0.5</sub>Pb<sub>0.5</sub>)<sub>3</sub>OSiO<sub>4</sub> ht  
Zn<sub>6</sub>In<sub>2.67</sub>S<sub>10</sub> 10H<sub>10</sub>  
Ag<sub>6</sub>Mo<sub>2</sub>O<sub>7</sub>F<sub>3</sub>Cl  
SiC 10H  
ZnS 10H<sub>2</sub>  
PbI<sub>2</sub> 14H  
CdI<sub>2</sub> 14H<sub>1</sub>  
CdI<sub>2</sub> 14H<sub>2</sub>  
CdI<sub>2</sub> 14H<sub>3</sub>  
CdI<sub>2</sub> 14H<sub>4</sub>  
CdI<sub>2</sub> 14H<sub>5</sub>  
CdI<sub>2</sub> 14H<sub>7</sub>  
CdI<sub>2</sub> 14H<sub>8</sub>  
CdI<sub>2</sub> 14H<sub>9</sub>  
Cu<sub>7</sub>Te<sub>4</sub>  
Agl 12H  
ZnS 12H<sub>3</sub>  
ZnS 12H<sub>2</sub>  
CdI<sub>2</sub> 16H<sub>1</sub>  
CdI<sub>2</sub> 16H<sub>2</sub>  
CdI<sub>2</sub> 16H<sub>3</sub>  
CdI<sub>2</sub> 16H<sub>4</sub>  
CdI<sub>2</sub> 16H<sub>6</sub>  
CdI<sub>2</sub> 16H<sub>7</sub>  
CdI<sub>2</sub> 16H<sub>8b</sub>  
CdI<sub>2</sub> 16H<sub>9</sub>  
CdI<sub>2</sub> 16H<sub>10</sub>  
CdI<sub>2</sub> 16H<sub>11</sub>  
CdI<sub>2</sub> 16H<sub>12</sub>  
BaVO<sub>2.5</sub>  
Na<sub>2</sub>In<sub>2</sub>Mo<sub>5</sub>O<sub>16</sub>  
CdI<sub>2</sub> 18H<sub>1</sub>  
CdI<sub>2</sub> 18H<sub>2</sub>  
CdI<sub>2</sub> 18H<sub>4</sub>  
CdI<sub>2</sub> 18H<sub>5</sub>  
CdI<sub>2</sub> 18H<sub>6</sub>  
CdI<sub>2</sub> 18H<sub>6b</sub>  
CdI<sub>2</sub> 18H<sub>7</sub>  
CdI<sub>2</sub> 18H<sub>8</sub>  
CdI<sub>2</sub> 18H<sub>9</sub>